

DATE : 10.05.2017

PRODUCT NAME : MEDITERAN

APPLICATION AREA : UPHOLSTERY

COMPOSITION : % 96 Polyester, % 4 PU

TEST TYPES/	UNIT	WARP	WEFT	TEST METHOD
TENSILE STRENGTH /	N	>350	>350	ISO 13934- 2
TEAR STRENGTH /	N	>20	>20	ISO 13937-2
ABRASION RESISTANCE /	cycles	>25000		ISO 12947
PILLING /	cycles	>25000		ISO 12945 - 2
COLOR FASTNESS TO LIGHT /	blue wool /	4		ISO 105-B02
WEIGHT /	gr / m ²	340 ± 15		ISO 2286 - 2
COLOR FASTNESS TO RUBBING/	-	Wet min.3/4 - Dry min.4		ISO105-X12
EASY CLEAN /	-	YES /		-
WIDHT /	cm	141 ± 1		-
ROLL LENGTH /	m	35 ± 5		-

CLEANING INSTRUCTIONS /

Liquid Stains: Blot the liquid stain gently with a high-absorbent material. Pat dry the area gently with a dry material to remove the remaining humidity (cotton cloth, paper towel, etc....), If the stain from the spill remains, remove the stain with a soapy cloth without diffusing the stain. After each rubbing motion, refresh the clean soapy cloth in order to prevent soiling.

Solid Particles: Romove the excess soiling with ultimate care without diffusing. Remove the solid particle from the fabric surface with the help of a soft spatula. To remove dust, use a vacum cleaner or a soft brush. The remaining stains should be removed by rubbing with a soapy cloth in circular motion.

Ball-point pen and similar difficult stains : Dampen a clean cotton cloth in a white soap solution. Rub the stain off gently. Clean the surface with the damp cloth and leave the fabric for drying

Alcohol derives, Petroleum and alkali based solvents should not be used for cleaning. After all cleaning processes, the drying should be done with a low temperature blow dryer in large circular motion or the fabric should be left for natural drying. After drying, misoriented and damaged piles should be fixed with a soft brush.



This is Valid For All Colours Of The Product /