



No.7010/20

LABORATORY ANALYSIS

Skopje, 03.02.2020

1. GENERAL DATA

- 1.1 Product: Upholstery fabric
- 1.2 Article: TOLEDO
- 1.3 Test ordered by: "FOKUS" Nikola DOOEL - Skopje, Macedonia
- 1.4 Sampling: Delivered sample
- 1.5 Technical documentation: MKC, EN standards
- 1.6 Place and date of inspection: Skopje, February 2020
(Report No:025T/20)

2. TEST RESULTS

(from sample delivered by test orderer)

<u>Laboratory testing</u>			
	testing parameters	units	test results
2.1	Maximum force using the strip method (CRE): - warp - weft (MKC EN ISO 13934 -1:2014, EN ISO 13934-1:2013)	N	700 427
2.2	Elongation at maximum force: - warp - weft (MKC EN ISO 13934 -1:2014, EN ISO 13934-1:2013)	%	51 87
2.3	Color fastness to rubbing: - dry - wet (MKC EN ISO 105 -X12:2016, EN ISO 105 -X12:2016)	grade	4 - 5 4
2.4	Determination of resistance to surface wetting (spray test): (MKC EN ISO 4920:2013, EN ISO 4920:2012)	grade	ISO 1
2.5	Abrasion resistance by the Martindale method - Part 2: Determination of specimen breakdown: (MKC EN ISO 12947-2:2017, EN ISO 12947-2:2016)	rubs	50 000 (no broken threads)

Prepared by:
Liljana Peovska
Laboratory manager

Approved by:
Svetlana Kanevce
Expert

- *) unaccredited method
**) external service

